

NC GRANOL SPECIFICATION E9(E950)

TESTS	SPECIFICATION
Nitrogen Content (%)	11.8-12.2
Viscosity (DIN 53179)	400±25CPS
B&J Stability Test in 132 ± 0.2 °C (ml/gr)	MAX 1.5
Moisture(%)	MAX 2
%Plasticizer (DBP or Dop)	20 ± 2 %
Acidity % (as H2SO4) Dry NC	MAX 0.065

Measuring viscosity according DIN 53179:

Measuring instrument: Hoesppler viscometer precisin model,ball4 with viscosity solution (see I)

I:For preparation viscosity solution mixing 9% by weight dry solid without plasticizer NC E9(E950) with 91% by weight solvent.

(solvent:95% by weight Acetone +5% by weight water)

Measuring temperature: 25°C

Standard range for viscosity according DIN53179:400cps ± 25cps

Main Applications :

Protective coating for polished metal surface, leather finishes, adhesives cement,pencil lacquers,Bronzing lacquers, Impregnating lacquers, finishing lacquers.



Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,

Shahnazari Ave, Madar SQ, Tehran, Iran

Tel: +9821 2225 69 21 Fax:+9821 2225 91 71

Email:info@caspianro.com

Website: www.caspianro.com