

NITROCELLULOSE SOLUTION NC 2003-40

Composition	%
Nitrocellulose 560 alcoholic	52
Nitrocellulose 950 alcoholic	5
Buthyl acetate	15
Ethyl acetate	10
Methyl acetate	8
Toluene	10

Specifications	
Solid content ASTM D 1644	40%
Viscosity at 20 ° c with cup 4 (1 unit Lacquer + 2 unit butyl acetate)	45-65 sec
Density at 25 ° c ASTM D 1475	0.94±0.01 gr/cm ³
Colour (Gardner colour standard) 1933	MAX 3 gardner
Flash point ASTM D 93	<20 ° c

Physical properties

viscous, colour, less or pale yellow liquid

odour of the used solvents

Very good adhesion and flexibility, excellent gloss retention used for, wood coatings, automotive repair paints, industrial coatings, leather coatings.



Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st,
Shahnazari Ave, Madar SQ, Tehran, Iran
Tel: +9821 2225 69 21 Fax: +9821 2225 91 71
Email: info@caspianro.com
Website: www.caspianro.com