NC GRANOL SEPCIFICATION E27(E400)

TESTS	SPESIFICATION
Nitrogen Content (%)	11.8-12.2
Viscosity (DIN 53179)	400±25CPS
B&J Stability Test in 132 \pm 0.2 $^{\circ}$ C (ml/gr)	MAX 1.5
Moisture(%)	MAX 2
%Plasticizer (DBP or Dop)	20 ± 2 %
Acidity % (as H2SO4) Dry NC	MAX 0.065

Measuring viscosity according DIN 53179:

Measuring instrument: Hoeppler viscometer precisin model,ball4 with viscosity solution (see I)

I:For preparation viscosity solution mixining 27% by weight dry solid without plastizier NC E22(E560) with 73% by weight solvent.

(solvent:95% by weight Acetone +5% by weight water)

Measuring temperature: 25°c

Standard range for viscosity according DIN53179:400cps ± 25cps

Main Applications:

Wood lacquers, combination lacquers, dipping lacquers, glossy finishing lacquers, dipping lacquers, etc



Caspian Ro Chemical Co.

Head Office: Unit 12, No. 25, 2nd st, Shahnazari Ave, Madar SQ, Tehran, Iran Tel: +9821 2225 69 21 Fax:+9821 2225 91 71

Email:info@caspianro.com

Website: www.caspianro.com